



**Soundness of Aggregates Test Results**  
**NYSDOT Method, Magnesium Sulfate, 10 Cycles**

**Product:** Washed NYSDOT #2 Stone  
**Source:** West of Jeddo Creek-working 30' face  
**Plant:** 72" & 66" Spokane's Running  
**Client:** Shelby Crushed Stone, Inc.

**Project No:** 10-028  
**Lab ID:** 10-380  
**Date:** 08/19/10

<b>Sieve Size Range</b>	<b>Grading of Original Sample %</b>	<b>Weight of Test Fractions Before Test g</b>	<b>% Passing Designated Sieve After Test</b>	<b>Weighted Percentage Loss %</b>
2"-1"	0.5	0.0	NA	NA
1"-1/2"	98.1	616.2	12.2	12.0
1/2"-1/4"	1.1	0.0	NA	NA
1/4"-#10	0	0.0	NA	NA
<b>Totals</b>	<b>99.7</b>			<b>12.0</b>

Submitted by: Jeanne M. Asquith

Date: 8/19/2010